

# Stainless Spring 316

Hcai No.		Thick	Qty	Wt	Chemical Composition(%)													Mechanical Property									
		(mm)		(Kg)	C	Si	Mn	P	S	Ni	Cr	Mo	Cu	N					TS	EL	HV						
					*100	*100	*100	*1000	*1000	*100	*100	*100	*100	*PPM					N/mm2	%							
Spec	Min									1000	1600	200															
	Max									1400	1800	300		1000													
2F854		5.50	5	7825	3.8	34	156	25	2	1057	1659	203	24	223					550	65	143						